

ROMACOTE RED FUSION BONDED EPOXY COATING

SUBMITTAL INFORMATION



PRODUCT USED

Red Romacote complies with AWWA C213.

DESCRIPTION

U.L.

U.L. listed under sections QMFZ2 or DTOV2.

SURFACE PREP

Shot blast to white finish.

THICKNESS

Normally 8 to 12 mils. Up to 16 mils on request.

APPLICATION

Electrostatic spray or fluidized bed.

PROPERTIES

See manufacturer's specification sheet.

OPTIONS

Mil thickness and testing per AWWA C213 available on request.

This information is based on the best data available at the date printed above. Please check with Romac for any updates or changes.